

**Test Report No.:** 0244167764a 002

Page 1 of 4

**Client:** BenQ Corporation  
16 Jihu Road, Neihu, Taipei 114, Taiwan

**Test item(s):** Interactive Flat Panel

**Identification/** RP65\*K, RP70\*K, RP86\*K, RP65\*\*\*, RP75\*\*\*, RP86\*\*\*, VA650\*\*, VA750\*\*,  
VA860\*\*, CM\*\*0\*K\*, CP\*\*0\*K\*

**Model No(s):** ( \*could be 1 to 9, A-Z, Means different client code or sale region, no impact on  
Products' safety and EMC characteristics )

**Sample Receiving date:** 2019-07-25

**Delivery condition:** Apparent good, Samples tested as received

**Testing Period:** 2019-07-25 to 2019-08-06

**Test specification:**

**Test result:**

JIS Z 2801:2010  
Antibacterial products-Test for Antibacterial Activity and Efficacy

Please refer to page 3

Remark: Please be kindly informed that all the content recorded in the captioned report 0244167764a 001 is cancelled and now superseded by 0244167764a 002.

For and on behalf of  
TÜV Rheinland (Shanghai) Co., Ltd.



2019-09-24

**Eason Lu / Supervisor**

Date

Name/Position

Test result is drawn according to the kind and extent of tests performed.  
This test report relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

Test Report No.: 0244167764a 002

Page 2 of 4

**Material list**

Item: Material

Material No.	Material	Color	Location
M001	Glass+Coating	Transparent+Transparent	Refer to 0244160802a 001 M001

## Antibacterial Activity and Efficacy Testing

### Test method:

JIS Z 2801:2010 Antibacterial products-Test for Antibacterial Activity and Efficacy

### Test Result

<b>Test No.:</b> T001					
<b>Material No.:</b> M001					
Organisms - Bacteria	Control specimen (Contact time: Initial, "A")	Control specimen (Contact time: 24hrs, "B")	Tested specimen (Contact time: 24hours, "C")	Antibacterial activity(1*)	Antibacterial effectiveness(2*)
<i>Escherichia coli</i> (ATCC No. 8739)	4.1	6.5	<0.8	>5.7	Yes
<i>Staphylococcus aureus</i> (ATCC No. 6538P)	3.9	6.6	<0.8	>5.8	

Abbreviation: < denotes less than  
> denotes more than

#### Where

A: Average of the number of viable cells of bacteria immediately after inoculation on control specimen.

B: Average of the number of viable cells of bacteria on control specimen after 24hrs incubation period.


C: Average of the number of viable cells of bacteria on the antimicrobial test specimen after 24hrs incubation period.

**Remark(s):**

- 1\*. Antibacterial activity calculated from (Log B- log C).
- 2\*. The value of antibacterial activity more than 2.0 indicates the tested product with antibacterial effectiveness.
- 3\*. The result should be based on the submitted sample only, the nature and processing of sample should not be taken into account.

\*\*\*END\*\*\*

**Sample Photo:**



-END-